

| Grass | 7 | V / | C-1 | |
|--------|------|-------|--------|--|
| 11racc | /nne | yarn/ | l ninr | |

Grass Zone Denier

Thatch Zone Yarn/Color

Thatch Zone Denier

Grass Zone Yarn Shape

Finished Pile Height

Finished Pile Weight

Backing

Tuft Gauge

Total Weight

Tuft Bind

Permeability

Features

Test Data

PE / Field Green

5,040/8

Nylon / Dark Green

6,000/6

Slit-Film XP Pro Plus

1"

1

65 oz.

TTC G16 Reinforced Fiberglass

3/16"

102 oz.

> 8 lbs.

> 20 inches per / SY

No Turf Delamination, Pre-installed Velcro attachment system

ASTM Certified F355-01 Class 1 Fire Rating

SYNMod

This modular turf system is designed for multi-use facility and sports applications such as Crossfit™, indoor soccer, Lacrosse, and more. Combined with closed-cell shock pad technology and a hook-and-loop fastener system, this portable turf system can easily be used over and over.



5 Year Warranty



Reinforced Fiberglass Backing



Use Indoors or Outdoors



Not to scale. For illustration only.

RECOMMENDED USES























| Primary Yarn Polymer | Polyethylene | | |
|----------------------------|-----------------------|--|--|
| Yarn Cross Section | Slit-Film XP Pro Plus | | |
| Standard Color | Field Green | | |
| Fabric Construction | Tufted | | |
| Second Yarn Polymer Thatch | Nylon | | |
| Secondary Yarn Color | Dark Green | | |

| Primary Backing | Reinforced Fiberglass | |
|---------------------------------|-----------------------|--|
| Cushion | 15mm | |
| PE Yarn Denier / Ends | 5,040 / 8 | |
| Texturized Thatch Denier / Ends | 6,000 / 6 | |
| Warranty Period | 5 Years | |

| Finish Fabric | English S | English System | |
|------------------------------|-----------|----------------|--------|
| Nominal Specification | Value | Units | Method |
| Pile Height (Nominal) | 1 | inches | D-5823 |
| Face Weight | 65 | oz/yd² | D-5848 |
| Total Fabric Weight | 102 | oz/yd² | D-5848 |
| Primary Backing Weight | 7 | oz/yd² | D-5848 |
| Backing Cushion | 30 | oz/yd² | D-5848 |
| Tuft Bind | > 8 | lbs. | D-1335 |
| Grab Tear Strength (Average) | > 200 | lbs. | D-5034 |
| Total Yarn Linear Density | 11,040 | Denier | D-1577 |
| Elongation to Break | > 30 | % | D-2256 |
| Yarn Breaking Strength | > 20 | lbs. | D-5793 |
| Machine Guage | 3/16 | inches | D-5793 |
| Flammability | Passed | - | D-2859 |
| Water Permeability | 60.05 | in/hr | D-1551 |
| Panel Width | 4 x 7-1/2 | ft | - |







